A GUIDE FOR PROFESSIONAL CONCRETE CUTTERS



The purpose of this publication is to let you know how important you are to this company, what is expected of you and to give you basic information on the tasks you may be performing.

The major difference between the successful professional cutter and the one destined to go out of business is the skill and abilities of its' field operators-YOU. You are the most important part of this business and as an operator you affect two thirds of the costs of running it. Mistakes made in cutting operations, accidents and attitude can put profit on the bottom line or the company out of business.

We know that you want to learn, improve and make yourself more valuable to the company, your family and yourself. To be a better cutter you should know the traits of a good field operator. Think about these traits, how you compare, and how you can improve on those which you are weak.



CONTENTS:

1-2	TRAITS OF A GOOD OPERATOR
3	HOW DOES AN OPERATOR EFFECT PROFIT
4	CORE DRILLING
5	FLAT SAWING
6	WALL SAWING
7	WIRE SAWING
8	CHAIN SAWING
9	HOW DIAMOND CUTTING TOOLS WORK
10	FACTORS THAT EFFECT PERFORMANCE
11	SPEEDS, FEEDS AND NOMENCLATURE
12-14	TROUBLE SHOOTING DIAMOND BLADES
15	TROUBLE SHOOTING DIAMOND CORE BITS
16	DIAMOND BOND PROBLEMS
17	EQUIPMENT ANCHORING
18	MECHANICAL ANCHOR GUIDE
19	ADHESIVE ANCHOR GUIDE
20	CARBIDE BITS
21-22	LADDER SAFETY
23	CORDS & POWER
24	HOW TO SELECT A GENERATOR
25	SAFETY SYMBOLS
26	CONVERSION CHART
27	AVERAGE WEIGHTS OF MATERIALS

THE TRAITS OF A GOOD OPERATOR



1. GOOD COMMUNICATOR- is able to quickly and clearly have the customer understand what he can and cannot do. A good communicator must be able to describe situations and problems found in the field to an office supervisor or to others at the office.

2. HIGH DEGREE OF COMMON SENSE - This is the ability to know what to do and most importantly what not to do in a situation. A good example of common sense is not to run an electric core rig while standing in 10 inches of water.





3. POSITIVE ATTITUDE - Maintaining a "Can Do" positive attitude is not only a reflection of the operators ability to get the job done but tells the customer that it will be done right. A positive attitude means keeping your problems, be they personal or business, to yourself. It is the foundation of being a true professional.

4. DISCIPLINED - Being on time, sticking to the schedule and doing what has to be done to complete the job requires discipline. Discipline and a positive attitude go hand in hand.





5. NEAT - You are not just a cutter. You are a representative of your company. If you have holes in your pants, a dirty shirt, are operating dirty equipment or leave a dirty job site after cutting, it tells the customer that this is the way your company runs it's business. We all know that this is not true !

6. DETAIL ORIENTED - Keeping accurate records of the footage cut and the time on the job is as important as your paycheck. Guessing at what you have done can mean a loss of profit, the overcharging of the customer and eventually the loss of your job. Being detail oriented applies to all record keeping - footage cut , holes drilled, time on the job, maintenance of equipment and what spec diamond tool was used on the job.





7. ABILITY to ADAPT, IMPROVISE AND OVERCOME - is the mark of a true professional. It means that you are still able to do the job even though it is not what you thought it was supposed to be. It means finding a way to drill that 24" hole vertically when you thought it was on the deck. It means fixing the equipment and getting the job done rather than quitting and going back to the shop.

8. STEADY PERSONALITY - This does not mean that you are always the good guy but that you are not subject to temper tantrums and wild swings in moods and personality. It means that you can be counted on to get the job done under almost any circumstances without losing your cool.





9. DESIRE TO LEARN AND IMPROVE - The more your learn, the more valuable you are to the company, to your family and to yourself. With each new acquired skill comes a higher degree of professionalism which will almost always find it's way into your paycheck.

10. UNDERSTANDS THE NEED FOR PROFIT - This is the most important trait. As an operator, you are delivering a service for a profit. Without profit there would be no company. Profit is what allows your company to buy more equipment and to pay you on a regular basis even though business may be slow. Profit allows your company to advertise it's services, to experiment with new equipment and techniques and to grow it's business. Profit is the reason you are working. You as an operator have a great effect on it.



HOW DO YOU EFFECT PROFIT ?



Unless you are a socialist, profit is not a dirty word. Profit is the reason you are here and profit is directly controlled by costs. You effect two thirds of the costs of running this company. Here are four areas where you can have a positive or negative effect on costs:

SAFETY - We can never over emphasize the need for safety, not because accidents and injuries cut profits and raise costs, but because they effect our most valuable asset - You. Hard hats, steel toed shoes, eye protection and back braces only work if they are used.



TIME - 1/3 of all costs are for your time. Taking too long or goofing off on the job cuts profit and irritates the

TOOLS - Diamond bits and blades can be very expensive. Using a bit or blade with the wrong specification wastes money. Abusing a bit or blade such as hitting it with a hammer to remove it will not be tolerated. Remember a 1% decrease in diamond cutting tool costs can put 10% profit on the bottom line jst as a 1% increase can take off 10% and jeopardize your job.





EQUIPMENT- Not repairing or failing to bring needed repairs to attention wastes both time and money. Using equipment that is not up to snuff is like diving into a swimming pool without knowing if there is any water in it.

EDUCATION - You are by nature equipment oriented, NOT process oriented. This means that you know how to operate the machinery but not what the diamond cutting tool is doing. Understandingthe process increases your performance and makes you more valuable.



customer.

UNDERSTAND NOT ONLY WHAT YOU DO BUT HOW YOU DO IT !

CORE DRILLING

As there are more variables in core drilling than in any other type of cutting, being competent in core drilling is the foundation of a good cutter.

Factors that affect bit performance and company profit:

Speed (RPM) -If the speed is too high the bit will polish. If the speed is too low the job will take too long.

Power is necessary to maintain the proper cutting speed. Efficient cutting means keeping the bit at the right speed.



Water - Not too little and not too much-The right amount removes slurry and keeps the cut clean.

Aggregate - You can't see it until you're done, but a good driller can feel the right speed and pressure to cut varying types.

Steel - slows the cutting process. Maintaining drill motor speed is important. DON'T PUSH THE BIT TOO HARD !- MAINTAIN SPEED !

Bond Specs - Too hard and it takes too long. Too soft and it costs too much.

Proper Alignment - is necessary for good bit life. This means the rig must be properly anchored. A rig can be anchored with concrete anchors, vacuum or a post jack.

STANDING ON THE RIG IS DANGEROUS AND NOT ACCEPTABLE ! Core Rig Maintenance -performance, speed and bit life will mean little if your rig has bad shims, bearings and hold down devices.

RECOMMENDED HORSE POWER					
	BY BIT DIAMETER				
	Bit	Min.	Min.		
	Diameter	AMPS	HP	GPM	
	1"-4"	13	1-2	-	
	5"	15	2	-	
Ø	6"	15	2	-	
dĩh	7"	15	2-3	-	
	8"	15	2-3	-	
	10"	18	2-3	-	
	12"	18	3	-	
	14"	20	3	-	
	16"	*		-	
	18"	*		8-10 @ 1500 PSI	
	20"	*		8-10 @ 1500 PSI	
	24"	-		8-10 @ 1500 PSI	
	26"	-		8-10 @ 1500 PSI	
	30"	-		12-15 @ 2000 PSI	
	32"	-		12-15 @ 2000 PSI	
	34"	-		12-15 @ 2000 PSI	
	36"	-		15-20 @ 2500 PSI	
	40"	-		15-20 @ 2500 PSI	
	42"	-		15-20 @ 2500 PSI	
* Not recor	* Not recommended for 120 Volt Use 220V 0r Hi-Cycle machine				

RECOMMENDED CORE DRILLING SPEEDS

	Bit Diameter	Minimum RPM	IDEAL RPM	Maximum RPM
<i>c</i> ₹	1"	2400	3200	4000
	2"	1200	1600	2000
a ///	3"	800	1050	1300
	4"	600	800	1000
	5"	475	640	800
M Coort	6"	400	530	665
~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~	7"	340	450	600
	8"	300	400	500
	10"	240	320	400
	12"	200	265	330
	14"	170	225	285
	16"	150	200	250
	18"	130	175	220
	20"	120	160	200
	24"	100	130	165
	26"	90	125	150
	30"	80	105	130
	32"	75	100	125
	34"	70	95	120
	36"	65	85	110
	40"	60	80	100
	42"	55	75	95

# FLAT SAWING

Successful flat sawing is a combination of blade selection, blade speed and common sense.

Pay Attention ! -The saw does not follow the cut itself- you have to guide it ! - Stay with the controls.

Water -is the blade's life and death. Don't be sparing with it . When road sawing keep the hose out of the traffic lane. Never gravity feed the water to the cut.





Always step cut - Make a 1" cut as your guide cut- Never cut full depth on the first pass.

Blade Speed -Always match the RPM of the saw to the diameter of the blade . Running a bladeat higher than recommended speed is dangerous. At worst the blade could fly apart and at best it reduces cutting effiting efficiency of a blade is at approximately 12,000 SFPM (surface feet per minuite) or 150 Miles Per Hour. PRODUCTIVITY IS <u>NEVER</u> INCREASED BY INCREASING BLADE SPEED !



Listen to the engine- You'll be able to tell when a blade is bouncing, the belts are slapping (loose) and when the blade is lifting itself out of the cut.



RECOMMENDED
BLADE RPM & MAXIMUM DEPTH OF CUT

Blade	Operating	Blade	Maximum
Diameter	RPM	Collar	Depth of Cut
14"	2900	4-1/2"	4-3/4"
16"	2600	4-1/2"	5-3/4"
18"	2600	4-1/2"	6-3/4"
20"	2450	4-1/2"	7-3/4"
24"	1950	4-1/2"	9-3/4"
26"	1950	4-1/2"	10-3/4"
30"	1650	6"	12"
36"	1400	6"	15"
42"	1050	6"	18"
48"	850	8"	20"
54"	775	8"	23"

# WALL SAWING

## Accuracy is the key to profitable wall sawing.

Track Setting - Accurate track setting is critical. Right Blade - The bonds used in wall saw blades are made not only for specific materials but different types of saws as Make sure you have the right blade for the job. Speed - Wall saws in general have less horsepower than other types of saws. Maintaining the right speed means paying close attention to the saw- you'll be able tell when cutting concrete or rebar. Make sure the blade

is running at the correct RPM. Don't over speed the blade. Water - is always important, especially when you are on a wall. Keep the pressure up !





Step cut- Don't over cut ! - Proper step cutting minimizes the cost per inch foot of cut and maximizes blade life. Step cutting increases the horsepower available to the blade and allows creased water flushing.

in-



Don't cut the branch you are standing on and make sure it is properly secured !

* Plan your cuts so you and your equipment are not on a piece when it breaks loose.

- * Insure that the blade is running in the proper direction.
- * Make sure the blade is in good condition with no cracks, nicks or flaws.
- * Use only steel centered wet cutting diamond blades.
- * Do not use high speed steel blades, carbide tipped blades or abrasive blades.
- * Always keep the blade guard in place and in good condition.
- * Always keep all parts of your body away from the blade.
- * Avoid getting in a direct line with the blade.
- * Make sure the track is securely anchored and track stops are installed.
- * Insure there are no electric, water or gas lines in the area you are cutting.
- * Do not operate the saw near combustible materials or fumes.

RECOMMENDED BLADE RPM & MAXIMUM DEPTH OF CUT

	Blade	Operating	Blade	Maximum
[	Diameter	RPM	Collar	Depth of Cut
	14"	1500	5"	4-1/2"
	16"	1500	5"	5-1/2"
	18"	1500	5"	6-1/2"
	20"	1500	5"	7-1/2"
	24"	1450	5"	9-1/2"
	26"	1450	5"	10-1/2"
	30"	1400	5"	12-1/2"
	36"	1300	5"	15-1/2"
	42"	950	5"	18-1/2"
	48"	850	5"	21-1/2"
	54"	700	5"	24-1/2"
	60"	625	5"	27-1/2"

# WIRE SAWING

Safety- is the key to profitable wire sawing.

- * Rope off the area in front of and behind and even below the job.
- * Secure the saw. It must be anchored and not weighted down.
- * Always keep the wire guard in place and in good condition.
- * Inspect the wire frequently for damage, frayed sections, missing beads, flat spots or weak connection points.
- * Always keep all parts of your body away from the wire
- * Avoid getting in a direct line with the wire.





Wire Twist- The number of twists in the wire is critical for maximum bead life. Start with one twist for every three feet of wire. Increase the number of twists per the chart below. These additional twists will assure that the beads wear round and give maximum life . While twisting this is a good time to look for flaws in the cable such as broken strands.

RECOMMENDED WIRE TWIST						
	Wire	Wire	Wire	Wire	Wire	
Wire	Diameter	Diameter	Diameter	Diameter	Diameter	
Length	.440"	.425"	.410"	.395"	.380"	
25'	8	9	10	11	12	
50'	17	19	21	23	25	
75'	25	28	31	34	37	
100'	33	36	40	44	48	

Wire Speed - is critical to good wire life. This table notes the correct wire speed for varoius flywheel diameters.





Beginning and Ending -Starting and finishing a cut produces the most strain on the wire. Give the wire a radius to start on. Don't start on a sharp edge.





Water- should be introduced at the beginning of the cut a n d contained throughout the cut. Vertical cuts should be directed as to allow the water to flow with gravity.

# **CHAIN SAWING**

Safety- A concrete chain saw can be just as dangerous as a wood cutting chain saw.

- * Never chain saw where you do not have sure footing and cannot face the cut without over extending your reach.
- * Always run the chain in a forward direction. Running the chain backwards reduces chain life and can cause serious injury.
- * Make sure hydraulic hoses are connected properly between the saw and power pack.
- * Avoid pinching the bar and chain in the cut.
- * Check for electrical wiring, gas or water lines near the cuttting area.
- * Inspect the chain frequently for damage and proper tension.
- * Make sure the drop out section is properly secured before making your final cut.
- * Rope off the work area.
- * Wear proper safety equipment including: Eye protection, boots, gloves, hard hat, hearing protection and rain suit.





Plan Your Cuts- Outline each cut with a marker for a visual cutting guide.

Water Pressure- must be maintained at a minimum of 80 PSI.





## Cutting Tips-

- Use Wall Walker for constant chain feeding.
- * Minimize the number of plunge cuts.
- Never exceed 8 gpm @ 2500 psi
- * Expect less chain life in steel reinforcing.
- Select the correct chain type for the job and material.
- Check and maintain proper chain tension
- For long vertical/horizontal cuts, score line first for guides.

## **DIAMOND CUTTING TOOLS**

## **TYPES OF DIAMOND BLADES**



A diamond blade is a circular steel disc with a diamond bearing edge. The edge or rim can have either a segmented, continuous or serrated rim configuration.

The blade core is a precision- made steel disc which may have slots called "gullets". These provide faster cooling by allowing water or air to flow between the segments. These slots also allow the blade to flex.

Blade cores are tensioned so that the blade will run straight at the proper cutting speed. Proper tension also allows the blade to remain flexible enough to bend slightly under cutting pressure and then go back to it's original position.

Diamond segments or rims are made up of a mixture of diamonds and metal powders. The diamonds used in bits and blades are man-made (synthetic) and are carefully selected for their shape, quality, friability and size. These carefully

with a powder consisting of metals such as cobalt, iron, tungsten, carbide, copper and other materials. This mixture is then molded into shape and then heated at temperatures from 1700° to 2300° under pressure to form a solid metal part called the "bond" or "matrix". The segment or rim is slightly wider than the blade core. This side clearance allows the cutting edge to penetrate the material being cut without the steel dragging against the sides of the cut.

There are several methods of attaching the segments to the steel core. Brazing - Silver solder is placed between the segment and the core and then heated until the solder melts and bonds the two together. This method is used for wet cutting blades only. Laser welding - The diamond segment and steel core are welded together by a laser beam . Mechanical bond - A notched, serrated or textured blade core may be used to "lock" the diamond rim or segments onto the edge of the blade. Mechanical bonds usually also include brazing or other metallurgical bonding processes to hold the rim or segments in place.

## HOW DO DIAMOND CUTTING TOOLS WORK ?



Diamond blades don't cut they grind ! The exposed diamond crystals do the grinding work. The metal matrix or bond holds the diamonds in place. Trailing behind each exposed diamond is a "bond tail" which helps to support the diamond. As the blade rotates through the material the exposed surface diamonds grind

After several thousand passes through the material being cut the exposed diamonds begin to crack and fracture. The matrix holding the diamond also begins to wear away.





Eventually the diamond completely breaks up and it's fragments are swept away with the material that it is grinding.

As the old diamonds are worn down they are replaced by new ones and the process continues until the blade is worn out.



## FACTORS THAT EFFECT PERFORMANCE

The following factors effect the performance of a concrete cutting blade or bit and should be considered when making your selection:

### COMPRESSIVE STRENGTH

Concrete may vary greatly in compressive strength which is measured in POUNDS per SQUARE INCH (PSI). Most concrete roads are approximately 4-6,000 PSI, while typical patios and sidewalks are about 3,000 PSI.

Concrete Hardness	s PSI	Application
Critically Hard	8,000 +	Nuclear power plants
Hard	6-8,000	Bridge piers
Medium	4-6,000	Highways
Soft		3,000 or less Side

## SIZE OF AGGREGATE

Larger aggregates tend to make a blade cut slower while smaller aggregates tend to allow a blade cut faster. The most common aggregate sizes are:

Size	
Pea Gravel	Usually less than 3/8" in diameter
3/4"	Sieved size
1-1/2"	Sieved size

## **TYPE OF SAND**

Sand is the component of the mix which determines the abrasiveness of the concrete. Sand can either be "sharp" (abrasive) or "round" (non-abrasive). Crushed sand or bank sand are usually sharp; river sand is usually round.

#### HARDNESS OF AGGREGATE

There are many different types of rock used as aggregate.

Generally hard aggregate breaks down the cutting diamonds faster which means the bond must be softer to expose new diamonds. Softer aggregate generally does not break down the cutting diamonds as quickly and therefore requires a harder bond to hold the diamonds in place to use their full potential. The Mohs' scale is used to

Mohs' Range	Description	Aggregates
8-9	Critically hard	Flint, Chert, Trap Rock,
Basalt		
6-7	Hard	River Rock, Granites,
Quartz,		Trap Rock
4-5	Medium/Hard	Granites, River Rock
3-4	Medium	Limestone, Sand Stone,

#### **REINFORCING STEEL**

Steel reinforcing tends to make a blade cut slower. Less reinforcing allows a blade to cut faster. Heavy rebar can also result from different grades of steel. Typical rebar is grade 40 but grade 60 is also common. Rebar gauges are in eights of an inch. #4 is 1/2" diameter, #5 is 5/8" diameter etc.

Size	Examples
Light	Wire mesh, single mat.
Medium	#4 rebar, every 12" on center each way (OCEV Single mat , Wiremesh, multi-mat
Heavy	#5 rebar, 12" OCEW, single mat. #4 rebar, 12" OCEW, double mat

#### GREEN OR CURED CONCRETE

The drying or curing of concrete greatly affects how the concrete will interact with a diamond blade. Green concrete is freshly poured concrete that has not yet cured. It is softer and more abrasive than cured concrete. A harder bond with undercut protection should be used in this application until it is cured at which point a softer bond would be appropriate. The definition of green concrete can vary widley. Water, temperature, moisture in the aggreagate, time of the year and the amount of water in the mix all influence the curing time. It is generally

#### VARIABLES

			RESULTS		
VARIABLES		CHANGE	CUTTING SPEED	BLADE LIFE	
	Segment Bond Hard-	Harder	Slower	Longer	
	ness	Softer	Faster	Shorter	
		Lower	Slower	Longer	
The Plade	Diamond Quality	Higher	Faster	Shorter	
пе ваче		Lower	Slower	Longer	
	Diamond Concentra-	Higher	Faster	Shorter	
	tion	Thicker	Slower	Longer	
	1011	Thinner	Faster	Shorter	
	Segment Width	Lower	Slower	Longer	
The Saw	Segment math	Higher	Faster	Shorter	
THE Saw	Horsepower	Higher	Slower	Longer	
		Lower	Faster	Shorter	
	Blade Speed	Higher	Slower	Longer	
	Bidde Bpeed	Lower	Faster	Shorter	
The lob	Water Volume	Deep	Slower	Longer	
1110 500		Shallow	Faster	Shorter	
	Cutting Depth	Lower	Slower	Longer	
	cutting Deptil	Higher	Faster	Shorter	
	Cutting Pressure	Harder	Slower	Longer	
	cutting ressure	Softer	Faster	Shorter	
Tho	Material Hardness	Less	Slower	Longer	
me	Material Haraness	More	Faster	Shorter	
Material	Material Abrasiveness	Larger	Slower	Longer	
	Material Abrasiveness	Smaller	Faster	Shorter	
	Aggrogato Sizo	More	Slower	Longer	
	Aggregate Size	Less	Faster	Shorter	

## DIAMOND CUTTING TOOL FACTS

#### and OPERATING SPEEDS Blade Cutting Diameter Recom-Maximum Depth Concrete mended Safe Speed (RPM) Saw Blades Operating 12" 3-3/4" Speed (RPM) 4500 3900 14" 2900 4-3/4" 16" 5-3/4" 2900 3400 18" 6-3/4" 2600 3000 20" 7-3/4" 2600 2700 24" 2450 2250 9-3/4" 26" 10-3/4" 1950 2100 30" 1950 1800 12" 36" 15" 1680 1500 1400 1300 42" 18" 850 1100 48" 20" Quickie 775 Saw Blades 6300 12" 4" 14" 5" 4300 5400 Wall Saw 4300 Blades 3000 18" 6-1/2" 24" 9-1/2" 1500 2250 30" 12-1/2" 1450 1800 1400 1500 36" 15-1/2" 1300 42" 18-1/2" 1300 48" 21-1/2" 950 1100 850 Masonry Saw Blades 14" 5" 3900 18" 2550 3000 7" 20" 8" 2300 2900 Tile saw 2300 Blades 1-3/4" 10175 6" 8725 - 7" 2-1/4" 6050 8" 2-3/4" 5175 7650 9" 3-1/4" 4500 6800 10" 4025 6125 3-3/4" 3625 Power Hand 15000 Saw Blades 1" 9075 13300 4" 1-1/4" 8065 12000 4-1/2 1-1/2" 5" 7250 8725 2-1/2" 7" 3" 5175 7650 **RECOMMENDED DRY HOLE SAW OPERATING SPEEDS** Max RPM/Min RPM Blt Diam-Min. AMPS 6000/2300 6 eter 1" 6 6000/2300 1-1/4" 5000/1600 7 1-1/2" 5000/1600 7 1-3/4" 7 5000/1200 2" 7 5000/1200 2-1/4" 5000/1200 7 2-1/2" 7 5000/800 3" 10 5000/800

3-1/2"

4"

5"

10

10

10

5000/700

2500/700

2500/600

MAXIMUM BLADE CUTTING DEPTHS

#### RECOMMENDED CORE DRILLING SPEEDS

	Bit					
	Diam-	10 Amp	15 Amp	18 Amp	20 Amp	
	eter	Motor (RPM)	Motor (RPM)	Motor (RPM)	Motor (RPM)	
18	Up to 3"	1200	1200	1200	1200	
AL.	4"	-	900	900	1200	
- and the	5"	-	375	900	450	
ATT A	6"	-	375	375	450	
like	7"	-	375	375	450	
	8"	-	-	375	450	
	10"	-	-	375	450	
	12"	-	-	375	450	





## TROUBLE SHOOTING DIAMOND BLADES



BURNING



BLADE WILL NOT CUT (GLAZING)





WORN OUT-OF AROUND

CAUSE: Insufficient coolant (water) at the cutting surface of a wet cut

core bit or blade.

REMEDY: Increase the flow of water and check for proper direction of the

water to the cutting surface.

CAUSE: Insufficient cooling (air)

CAUSE: Blade is too hard for material being cut. (Wrong spec.) Bond will not wear away to expose new diamonds. REMEDY: Choose a softer bond.

CAUSE: Material being cut is too hard.

REMEDY: Dress or sharpen the blade with a soft concrete block or old

abrasive wheel to expose new diamonds. If continual dressing is needed change to a softer bond.

CAUSE: Insufficient power to permit blade to cut properly. REMEDY: Check and tighten belts and make sure adequate

CAUSE: On stone or masonry blades the material may not have been

held firmly which allowed the blade to twist or jam.

REMEDY: Material must be held firmly.

CAUSE: Overheating due to an inadequate supply of water. Look for burning or discoloration near missing seg-

ments.

REMEDY: Provide adequate supply of water.

CAUSE: Undercutting which wears away blade core and weakens the

weld between segment and core.

REMEDY: Increase water supply and if material being cut is very abrasive

switch to wear-resistant cores.

CAUSE: Worn shaft bearings on saw which allows blade to run eccentric. **REMEDY:** Install new bearings. Engine not properly tuned which causes "hunting". CAUSE: **REMEDY:** Tune the engine. CAUSE: Blade arbor hole is damaged. REMEDY: If blade is in good condition the core may be re-bored. CAUSE: Blade mounting arbor is worn or is the wrong size. REMEDY: Replace worn arbor busing or arbor shaft. CAUSE: Bond is too hard for material causing machine to "pound" at



UNDERCUTTING



LOSS OF TENSION



ARBOR OUT OF AROUND



EXCESSIVE WEARUNDERCUTTING

CAUSE: A condition in which the steel core wears at a faster rate than

the diamond segments. It is caused by highly abrasive material grinding against the core.

REMEDY: The blade core should be equipped with undercut

CAUSE: Blade is used on a misaligned saw.

REMEDY: Check for proper saw alignment.

CAUSE: Blade is excessively hard for the material being cut.

REMEDY: Correct bond spec.

CAUSE: Material slippage causing blade to twist.

REMEDY: Maintain a firm grip on material while cutting.

CAUSE: Undersize or mis-matched blade collars.

REMEDY: Minimum 3-7/8" - 4-1/2" on concrete saws, 6" Minimum on

blades over 30", 8" Miniumum over 48".

CAUSE: Blade used at improper RPM.

REMEDY: Check shaft RPM.

CAUSE: Improper mounting on arbor shaft allows collars to bend blade

when tightened.

CAUSE: Blade collar is not properly tightened allowing it to turn or rotate on shaft. REMEDY: Tighten collars. CAUSE: Worn or dirty collars which do not allow proper blade clamping. REMEDY: Clean and replace if necessary.

CAUSE:	Using the wrong blade spec. on highly abrasive materi-
als.	
REMEDY:	Change to a more abrasive resistant bond.
CAUSE:	Lack of sufficent coolant to the blade often detected by
	excessive wear in the center of the segment.
REMEDY:	Make sure water supply system is functioning properly.
CAUSE:	Wearing out-of-round accelerates wear. Usually caused



CAUSE: Blade is too hard for material being cut.
REMEDY: Change to softer bond.
CAUSE: Excessive cutting pressure, or jamming or twisting of the blade
REMEDY: The saw operator should use a steady even pressure without
twisting the blade in the cut.

CAUSE: Overheating through inadequate water supply or not allowing a dry

CORE CRACKS



CAUSE: Blade collars are not properly tightened or are worn out.

MISMOUNTING



SEGMENT CRACKS



UNEVEN SIDE WEAR

CAUSE: Blade is too hard for the material being cut. REMEDY: Use correct blade with a softer bond.

of

## TROUBLE SHOOTING CORE BITS

Too much feed pressure.

Aggregate is too hard.

REMEDY : Change to a softer bond.



GLAZING (Bit stops drilling or is very slow)



CAUSE: Too much feed pressure and not enough water.

pressure. Using an ammeter will help to control speed and

REMEDY: Repair the bit if possible. Ease up on feed pressure and increase water flow.

REMEDY: Open bit with abrasive material (Sand pot, concrete block, chop

**Reduce feed** 

pressure.

CAUSE: Aggregate is too hard.

BENT SEGMENTS



CAUSE: Steel reinforcing rod

REMEDY: Ease up on feed pressure (watch ammeter). Use a higher quality bit and increase the

water flow.

CAUSE:

CAUSE:

saw blade).

CAUSE: Not enough water too properly cool bit.

REMEDY : Increase water flow.

CAUSE: Drill rig is not properly anchored.

REMEDY: There are three ways of anchoring a core rig. STANDING ON IT IS NOT ONE OF THEM !.



CORE HÀNGS UP

CAUSE: Not enough water to remove slurry.

REMEDY: Remove bit and drive core out with a spike through the hub. Increase water

flow.

CAUSE: Core barrel is dented because of hammering on it to remove previous hung up



## **TROUBLE SHOOTING - DIAMOND PROBLEMS**



## CONCRETE ANCHORING - COMMON SENSE AND FACTS

CONCRETE ANCHORING IS A CRAFT. It is not a science. It is a craft because of the tremendous variables found in concrete, the tolerances of the carbide drills and anchors, the tools used to set them and most importantly the skill of the installer. As a craft it is imperative that the "craftsman" learn as much about the material, tools and conditions that he has to work with.

ALLOWABLE WORKING LOADS & MATERIAL STRENGTH. A quick look at the catalogs of various anchor manufacturers will have many scratching their heads. Some print the ultimate load while others state the maximum allowable load. Shown below are the performance charts on Drop-In anchors from three major manufactures which at first glance could be confusing and if not properly understood the cause of a costly anchor failure.

	2000 Cond	PSI crete	4000 Cond	) PSI crete	6000 Cone	) PSI crete
Anchor Size	Tension	Shear	Tension	Shear	Tension	Shear
1/4″	480	430	560	450	770	760
3/8″	790	990	1240	1060	1410	1480
1/2″	1000	1470	1690	1560	2550	2340
5/8″	1390	2220	2420	3050	2600	3400
3/4″	2210	3800	4010	4400	4100	5300

Bolt Size/ Threads Per Inch	Drill Bit Size	A Thread Depth	B Min. Hole Depth	Ultimate Pullout* Lbs.	Ultimate Shear* Lbs.
1/4"/20	3/8"	3/8"	1"	3,204	1,986
3/8"/16	1/2"	1/2"	1-5/8"	6,350	3,968
1/2"/13	5/8"	3/4"	2"	8,544	6,502
5/8"/11	7/8"	1"	2-1/2"	15,218	10,380
3/4"/10	1"	1-1/4"	3-3/16"	17,255	13,962

		COMPRESSIVE STRENGTH OF CONCRETE				
	i	2000	PSI	5000	PSI	
BOLT SIZE	NOMINAL DRILL BIT SIZE	LBS. TENSILE	LBS. SHEAR	LBS. TENSILE	LBS. SHEAR	
1/4	3/8	1560	1600	2,400	2,177	
3/8	1/2	3024	3640	4,200	3,950	
1/2	5/8	3634	6500	6,990	6,422	
5/8	7/8			9,750	12,500	
3/4	1			11,500	16,590	

It is imperative that the Allowable Working Load be determined with regard to the strength of the concrete and the particular cutting or drilling operation before hand. If the ultimate load is published the safe working load is 25% of the ultimate load (4:1) and this value must be matched with the strength of the concrete which can affect the performance of the anchor by another a factor of almost 3:1

ANCHOR FAILURE - With rare exception almost every anchor failure is caused by the operator. Not the anchor. Among the most prevalent mistakes in the sawing and drilling industry are:

- 1. Not fully expanding a drop-in anchor because the wrong setting tool was used or the operator simply "felt" that the anchor was set.
- 2. Setting a stud anchor at too shallow a depth because it was on top of a rebar.
- 3. Setting a capsule anchor by simply driving the threaded stud into the capsule and not spinning it. As the adhesive has not been mixed with the catalyst it will not set fully or not set at all.
- 4. Leaving an inordinate amount of dust in the hole when using an adhesive anchoring system. The adhesive bonds to the dust and the dust is bonded to nothing.
- 5. Using an anchor which does not have the capacity for the job. A particular anchor may be adequate on a horizontal surface but totally inadequate when used on a vertical one with the exaggerated component loads on equipment in this position.
- Using the wrong size carbide bit to drill the hole. The best example of this is using an old worn 5/8" bit for 1/2" anchors. The anchor is quick to install and just as quick to fail.



## MECHANICAL ANCHOR GUIDE



# ADHESIVE BONDED ANCHOR GUIDE

#### POURABLE ADHESIVE ANCHOR (Horizontal applications only)



Drill hole to proper depth.



Clean with a blow out bulb, wire brush, water pressure. Dust left in the hole acts as a lubricant and will reduce it's holding power.



Mix adhesive and pour correct amount per manufacturers instructions into the hole.



Insert threaded rod slowly into hole using a twisting motion.



Allow to cure recommended time before applying load.

#### CAPSULE ANCHOR



After drilling hole to proper depth clean with a blow out bulb, wire brush,water pressure.Dust left in the hole acts as a lubricant and will reduce it's holding power.



Insert capsule.



While rotating a chamfered stud with a rotary hammer or hammer drill drive it through the capsule. Remove the drill and setting tool from the stud



Allow stud to set until adhesive is cured which is dependent upon temperature.(20 minutes to 6 hours)



Drill hole to proper depth.



Clean with a blow out bulb, wire brush, water pressure. Dust left in the hole acts as a lubricant and will reduce it's holding power.



Injective adhesive unto the hole unitl it is ap-proximately one-half full (permanufacturers instructions)



Insert threaded rod slowly into hole using a twisting motion.



Allow to cure recommended time before applying load.

ADHESIVE ANCHOR (Hollow wall application)



After drilling hole to proper depth clean with a blow out bulb, wire brush, water pressure.



Fill wire screen with adhesive while withdrawing the nozzel.



Insert the filed screen completely into the cleaned hole.



Holding the tab on the screen insert the threaded rod with a slow twisting motion. Allow to set for appropriate cure time which is dependent on temperature.

# CARBIDE DRILL BITS



## LADDERS

## LADDER RATINGS

The American National Standards Institute (ANSI) adopted and issued a code of safety requirements for portable ladders. The code, last revised in 1982, sets out the properties and design specifications for wood (A14.1), metal (A14.2) and reinforced plastic (A14.5) ladders. Completed ladders must also be capable of passing a variety of test requirements as set out in the code.

ANSI TYPE *	DUTY RATING **	DESCRIPTION
TYPE 1A	300 lbs.	Extra Heavy Duty Industria
ΤΥΡΕ Ι	250 lbs.	Heavy Duty Industrial
TYPE II	225 lbs	Medium Duty Commercial
TYPE III	200 lbs	Light Duty Household

* OSHA essentially follows the guidelines set by ANSI. Therefore, industrial users should purchase and properly use Type 1A and Type 1 ladders to be in compliance with OSHA regulations. Type II and Type III are NOT permitted on the job site.

** The Duty Rating means that the ladder is designed to meet these loads with a safety factor of four (4) when set and used properly at 75-1/2° to the horizontal.

## LADDER SELECTION

Select the highest duty rating necessary to cover the total amount of the weight that will be applied to the ladder. Safety Equipment



MATERIAL	<u>ADVANTAGES</u>	DISADVANTAGES
WOOD	Low initial cost. Non-conductive. Good strength- to- weight ratio	Heavier and less durable than aluminium or fiberglass.
ALUMINUM	High durability. Weather resistant. Very high strength- to- weight ratio. Light weight.	Highly conductive. Corrodes in some environments.
FIBERGLASS	High durability. Non-conductive. High strength- to -weight ratio. Weather resistant.	Higher initial cost. Can be damaged by heat.
LA		LADDER TYPES
PULLEY FLY SECTION	END CAPS	SINGLE STEPLADDER- Has steps on one side and is a self supporting climbing tool for applications at low to medium heights. 3' to 16'. DOUBLE FRONT STEPLADDER - Has steps on both sides and is a self supporting climbing tool for low to
SIDE RAIL RUNG RUNG	PE REAR SIDE RAIL	medium heights. 3' to 16'. PLATFORM STEPLADDER - Provides a large platform to work on and is self supporting. TRESTLE LADDERS - May be used alone or with a second trestle ladder to support planking systems. Up to 16'. STRAIGHT LADDERS - A non self supporting single straight ladder section used for mid -range heights. 8' to 20'.
	REAR FOOT	EXTENSION LADDERS - A non-self supporting adjust- able ladder for mid-range to high work levels. 8' to 40'.
SHOE	FRONT FOOT 21	For further Information check with your ladder manufacturer or refer to ANSI A14 for additional guidelines.

LADDER MATERIALS

## LADDER SAFETY

DOinspect your ladder carefully----when you buy it and before DON'T use or repair a bent or damaged ladder. Send it back each use. Look for missing, damaged or loose parts. to the factory for repairs or replace it. DO make sure that working parts move freely and that there DON'T test a ladder by jumping on it. This could damage or are no missing nuts, bolts, rivets or locks. weaken the ladder, and you may slip or fall. DO follow label instructions. Start by carefully reading all DON'T use on slippery surfaces or uneven ground. labels. These instructions are gathered from years of experi- DON'T set up a ladder where it could possibly touch electrience and they are offered for your benefit. cal devices or wires. DO be sure that the ladder feet are on solid ground. DON'T set up a ladder on a wet or icy surface unless you tie DO wear shoes that have soles that do not slip. Make sure down the legs. they are free of mud, oil, or anything slippery. DON'T climb down a ladder with your back to the ladder, or DO check for frayed or damaged cords when using power carry a load in your arms. tools. Use only cords with grounded outlets. DON'T over-reach, lean to one side or stand on one foot. DO climb facing the ladder. Center your body on the steps. DON'T hurry or skip steps when geting on or off a ladder. Use a firm grip. If possible, have someone hold the ladder DON'T try to move a ladder while on it by bouncing "walking" the ladder. for you. DO keep your body centered on the ladder while working. DON'T leave a ladder unattended DO hold the ladder with one hand while working with the DON'T position the ladder where it blocks foot traffic or where other, whenever possible. it could be bumped by a door. DO keep children away from ladders while working. DON'T place a ladder on boxes, chairs, furniture, or other DO move materials with extreme caution. Be careful pushing things which are movable to try to climb higher. or pulling anything while on a ladder. DON'T climb from one ladder to another. DO use a ladder only when you are mentally and physically DON'T climb a damaged ladder. alert. DON'T climb a ladder when ill or physically alert. DO securley tie down the ladder when transporting it on a DON'T drop or throw ladders. DON'T use a ladder as a pry bar. vehicle. DO store ladders out of reach of children. DON'T use a ladder as a work bench. Hammering, sawing DO keep ladders protected from excessive heat and the and grinding can weaken key components. weather. DON'T use a ladder that has been exposed to fires, acids, DO keep your ladder in good condition. Keep it clean. caustics or other strong chemicals. DON'T paint a wood ladder. This can hide damage and can create a slippery surface. KNOW WHERE THE LAST STEP IS HOW TO CHOOSE THE RIGHT SIZE

لىرىنى مەرىكەت	4TH RUNG FROM THE TOP
	HIGHEST STANDING LEVEL
2 FEET	
	p

HEIGHT TO <u>SUPPORT POINT</u> to 9-1/2' Max.	USE THIS <u>LENGTH LADDER</u> 16'	MAX WORKING <u>LENGTH</u> 13'
From 13-1/2" to 17-1/2'	24'	21'
From 21-1/2' to 25'	32'	29'
From 28' to 31'	40'	35'

THE PROPER WAY TO SET	UP A LADDER

HEIGHT TO	HORIZONTAL DISTANCE FROM
GUTTER OR	SUPPORT TO LADDER <u>BASE</u>
<u>SUPPORT</u>	2-1/2'
9-1/2'	3-1/2'
13-1/2'	4-1/2'
17-1/2'	5-1/2'
21-1/2'	6-1/2'
25'	7'
28'	8'
31'	

## **CORDS & POWER**

DOUBLE INSULATED/GROUNDED TOOLS: A double insulated tool is one that has all the electrical parts of the motor insulated from each other and all gripping surfaces made of non-conductive materials. In essence there are two layers of insulation between the operator and the tool's electrical systems. Tools that are double insulated are not intended to be grounded and therefore are equipped with a two pronged plug. Three-pronged plugs are found on grounded tools and are electrically safe as long as the receptacle is properly grounded.

POWER: In general, the higher the amperage rating of a tool the more powerful the motor. This assumes that tools being compared have motors operating at the same efficiency. Efficiency is defined as a percentage which is obtained when comparing usable output amps (power) to the amps being drawn by the motor. Different motors and/or different manufacturers will not have the same efficiency. One tool manufacturer says 6 amps, another says 750 Watts and still another says 1 horsepower all for the same tool.....How does one make a logical comparison?

*WATTS = AMPS X VOLTS X 62% (AC apparent power)				
AMPS =	<u>WATTS</u> VOLTS			
1 HORSEPOWER	= 746 WATTS			
e power consumed by	the tool and not its			

*This is the power consumed by the tool and not its power output. Output Watts is the true measure of a tool's power.

GROUND FAULT INTERRUPTER: A device which protects both the worker and the tool against line ground faults (short circuits). It does this by detecting any imbalance in the current flow to and from the tool. If a ground fault should occur, the current imbalance will trip the G. F. I. before the



operator is shocked.

REC	COMMENI	DED GENE	RATOR SIZ	ES	
			GENERATOR	SIZE	
H.P.	AMPS.	PHASE	IN KILOWATS		
1/2-1	14	1ph		4	
1	15	1ph		5	
1-1/2	18	1ph		5	
2		1ph		6.5	
5		1ph		12	
7.5		1ph		20	
5		3ph		12	
7.5		3ph		25	
10		3ph		25	
15		3ph		30	
20		3ph		40	
25		3ph		50	
30		3ph		60	
40		3ph		80	

#### **RECOMMENDED POWER CORD GAUGE**

RATING (	OF TOOL		REG	QUIRED CORI	D GAUGE SIZE		
H.P.	AMPS	PHASE VOLTAG	GE UP TO 50'	50-100'	100-150'	150-200'	
1/3-1/4	7	1ph	125v	#18	#18	#16	#14
1/2	10	1ph	125v	#18	#16	#14	#12
3/4	13	1ph	125v	#16	#14	#12	#10
1	15	1ph	125v	#14	#12	#10	#8
1-1/2	20	1ph	125v	#12	#10	#8	#6
1-1/2	13	1ph	115v	#12	#10	#8	#6
1-1/2	6	1ph	230v	#14	#14	#12	#10
2	30	1ph	125v	#8	#6	#4	#2
2-1/2	21	1ph	115v	#10	#8	#6	#4
2-1/2	11	1ph	230v	#14	#12	#10	#8
5	23	1ph	230v	#10	#8	#6	#4
5	12	3ph	230v	#14	#12	#10	#8
5	6	3ph	460v	#14	#14	#12	#10
7-1/2	33	1ph	230v	#8	#8	#6	#4
10	24	3ph	230v	#10	#8	#6	#4
10	12	3ph	460v	#14	#12	#10	#8
20	52	3ph	230v	#6	#6	#4	#2
20	26	3ph	460v	#10	#8	#6	#4
25	58	3ph	230v	#6	#6	#4	#2
25	29	3ph	460v	#10	#8	#6	#4
30	37	3ph	460v	#8	#6	#4	#2
40	48	3ph	460v	#8	#6	#4	#2
50	62	3ph	460v	#4	#4	#2	#0

## HOW TO SELECT A GENERATOR

#### When selecting a power generator it is important that it is capable of meeting your energy requirements. Both starting and running !

DETERMINE THE STARTING WATTS REQUIRED - When a motor is first turned on, the power required to start the motor fan exceeds the power Hmmm... Hovequired to normally run the motor. The many watts do l really need to marks on the nameplate of the motor are and run this the full load running amps and not the higher starting amps. To determine the Regenerator size necessary use the following formulas.

> For single phase WATTS = Amps x Volts x 2

For three phase WATTS = Amps x Volts x 3.5

STARTING WATTS VS RUNNING WATTS -Most generators have an intermittent 25% overload capacity. IE: a 2,000 watt generator will carry a 2,500 watt load for a short period, such as during start up. Motors starting under a heavy load (such as air compressors, refrigeration systems and those which must bring a heavy cutting tool up to speed) will require significantly more wattage to start. This higher demand must be considered when estimating power needs. This is particulary important when more than one motor is used at one time.

#### EXAMPLE:

Motor	Starting Watts	<b>Running Watts</b>
3/4HP Air Compressor	4300	1250
71/4" Circular Saw	-	1500
11/2" Rotary Hammer	-	800
Light String (10-100 Watt Bulbs)	-	<u>1000</u>
		4550

In the above example, a 5,000 watt unit would be ample, but only when the air compressor was started before the other tools were started. If the other tools were in use and the air compressor started after they were on line the power requirement would jump to 7600 watts which the unit may not be capable of.

#### POWER OUTPUT VS ALTITUDE

Less oxygen at higher altitudes reduces engine efficiency and power output. Unless otherwise specified by the manufacturer the unit should be derated to the following values:

Alternato	or Peak	Altitud	de in fee	t above	sea lev	el	
<u>Rating</u>	Power	<u>2000' 300</u>	<u>0' 4000'</u>	<u>5000'</u>	<u>6000'</u>	<u>7000'</u>	
1250	1375	1275	1220	1155	1100	1048	980
1750	1925	1750	1690	1615	1540	1465	1385
2500	2750	2500	2420	2300	2200	2090	1980
3650	4160	3650	3650	3500	3300	3160	2980
4000	4400	4000	3870	3700	3520	3340	3170
5000	5500	5000	4840	4620	4400	4170	3960
7500	9000	7500	7500	7500	7200	6850	6480

#### APPROXIMATE POWER CONSUMPTION of VARIOUS CONSTRUCTION TOOLS & APPLIANCES

Window Fan Jigsaw **Belt Sander** Screwdriver Chain Saw Circular Saw (7-1/4"-8-1/4") Circular Saw (10") **Cutoff Saw** Poratble Band Saw 2.5 HP Masonry Saw Impact Wrench (1/2 & 3/4") Impact Wrench (1") 1/4" Drill 3/8" Drill 1/2" Drill 1" Drill 15 Amp Core Drill 18 Amp Core Drill 20 Amp Core Drill 1/2" Hammer Drill 5/8" Hammer Drill 3/4" Hammer Drill 7/8" Rotary Hammer 1" Rotary Hammer 1-1/2" Rotary Hammer 2" Rotary Hammer 1-1/8"/1-1/4" Breaker Water Pump 3000 GPH Water Pump 5000 GPH Water Pump 10000 GPH Water Pump 20000 GPH Wet Dry Vacuum Water Pump (Submersible) 3000 GPH Water Pump (Submersible) 5000 GPH Water Pump (Submersible) 10000 GPH Water Pump (Submersible) 20000 GPH Concrete Vibrator (3/4 HP) Concrete Vibrator (1HP) Concrete Vibrator (3HP) Air Compressor -3/4HP Air Compressor -1-1/2HP Concrete Saw - 5HP

#### MOTOR STARTING & RUNNING WATTAGE

	Universal* Induction** Capacitor Start* Motors Motors InductionMotor				
Motor	Running	Starting	Starting	Starting	
Size	Watts	Watts	Watts	Watts	
1/4	400	500	850	1050	
1/3	450	600	975	1350	
1/2	600	750	1300	) 1800	
3/4	850	1000	1900	2600	
1	1000	1250	2300	3000	
1-1/2	1600	1750	3200	4200	
2	2000	2350	3900	5100	
3	3000		5200	6800	
5	4800		7500	9800	

 Utilizes a commutator and is generally used in power tools and small appliances.
 ** Brushless motor that has a large starting torque with less starting current. Generally used on pumps, compessors, frezzers.

***An induction motor which uses capacitors to start (and in some cases run) the motor. Used on pumps, compressors and refrigeration equipment.

# SAFETY SYMBOLS



![](_page_27_Picture_2.jpeg)

Fall protection is mandatory Es obligatorio el uso de ropa adecuada

![](_page_27_Picture_4.jpeg)

Use in Well Ventilated Area Utilizzare in presenza di un'adeguata ventilazione

![](_page_27_Picture_6.jpeg)

Danger, Poison Exhaust Gas Peligro, gases de escape toxicos

![](_page_27_Picture_8.jpeg)

Do Not Use in Flammable Areas No usar en areas inflamables

![](_page_27_Picture_10.jpeg)

No Non-Working Personnel in Area Prohibido para personas ajenas a la obra

![](_page_27_Picture_12.jpeg)

Motor Off Parar el motor

![](_page_27_Picture_14.jpeg)

Keep All Guards in Place Mantenga siempre las protecciones de la hoja en su sitio

![](_page_27_Picture_16.jpeg)

Danger ! Keep Hands Away From Machinery Maquina peligrosa- Matenga manos y pies alejados de la maqunia

![](_page_27_Picture_18.jpeg)

No Smoking No fumar

![](_page_27_Picture_20.jpeg)

Please read the instructions for use prior to operating the machine for the first time. Antes de la puesta en marcha, lea detenidamente las instrucciones y familiarcese con la maquina.

![](_page_27_Picture_22.jpeg)

Prohibited Prohibicion

![](_page_27_Picture_24.jpeg)

Warning Triangulo de advertencia

![](_page_27_Picture_26.jpeg)

Wear Eye Protection Usar gafas de proteccion'

![](_page_27_Picture_28.jpeg)

Wear Head Protection Usar casco de proteccion'

![](_page_27_Picture_30.jpeg)

Wear Breathing Protection Usar mascara de proteccion'

![](_page_27_Picture_32.jpeg)

Ear Protection Use is Mandatory Es obligatorio el uso de proteccion['] auditiva

![](_page_27_Picture_34.jpeg)

Hard Hat is Mandatory Es obligatorio el uso de casco duro

![](_page_27_Picture_36.jpeg)

Safety shoes are mandatory Es obligatorio el uso de zapatos de seguridad

# CONVERSION CHART

MULTIPLY	BY	TO OBTAIN
Acres	0.404687	Hectares
Acres	1076.39	Square Yards
Board Feet	144 sq. in x 1	Cubic Inches
Dual a reel Continutors	3937	Inches
Cubic Feet	28.3170	Liters
Cubic Inches	16.38716	Cubic Centimeters
Cubic Meters	35.3145	Cubic Feet
Cubic Meters	1.30794	Cubic Yards
Cubic Yards	.764559	Cubic Meters
Degrees, Angular	.01/4533 (%5.22) x 5555	Radians Degreese Contigrade
Degrees, Fanrenneit	(°C x1 8) ±32	Degrees, Centigrade Degrees, Fabrenbeit
Foot-Pounds	.13826	Kilogram-Meters
Feet	30.4801	Centimeters
Feet	.304801	Meters
Feet	304.801	Kilometers
Gallons - U.S.	.13368	Cubic Feet
Gallons - U.S.	231.0	Cubic Inches
Gallons - U.S.	3.78513	
Horsenower-Metric	98632	Horsenower-US
Horsepower-U.S.	1.01387	Horsepower-Metric
Inches	2.54001	Centimeters
Inches	25.4001	Millimeters
Kilograms	2.20462	Pounds
Kilograms-Meters	/.233	FOOT-POUNDS Dounds nor Souther
Kilograms per Motor	671972	Pounds per Sq. Inch Pounds per Foot
Kilometers ner Sa. Meter	.204817	Lhs per Sa Foot
Kilometers	.62137	Miles
Kilometers	.53959	Miles-Nautical
Liters	.26417	Gallons
Meters	3.28083	Feet
Meters	39.37 1.00361	Inches Vards
Miles	1.60935	Kilometers
Miles	.8684	Miles-Nautical
Miles-Nautical	6080.204	Feet
Miles-Nautical	1.1516	Miles
Pounds	453.592	Grams
Pounds Dounds nor Foot	.453592	Kilograms Kilograms por Motor
Pounds per Sa Foot	4 88241	Kilograms per Sa Meter
Radians	57.29578	Degrees-Angular
Square Centimeters	.1550	Square Inches
Square Feet	.0929034	Square Meters
Square Inches	6.45163	Square Centimeters
Square Inches	045.103 247.104	
Square Kilometers	.3861	Square Miles
Square Meters	10.7639	Square Feet
Square Miles	259	Hectares
Square Miles	2.59	Square Kilometers
Ions-Metric	2204.62	Pounds
Tons Matric	.90421 1 10231	Tons-Short
Tons U.S.	40	Cubic Feet
Yards	.914402 26	Meters

## AVERAGE WEIGHTS OF MATERIALS

CONCRETE LBS. PER	CU. FT.		STONE	IBS		
Stone, reinforced	150		STONE	LDJ	17E	
Stone, plain	44		Granite		1/5	
Slag plain	130		Limestone		105	
Cinder reinforced	100-115		Marble		165	
Cindel, Telmorced	100-115		Sandstone,	bluestone	147	
			Slate		175	
LIGHT WEIGHT CONCRETE	LBS. PER CU. FT	Г.				
Concrete Aerocrete	50.90		WOOD (12%	moisture content)	LBS. PER CU. FT.	
Concrete, Aerocrete	50-00 60		Birch, red oa	ak	44	
Concrete, Cindel III	00 95 100		Cedar, nortł	nern white	22	
	65-100 75		Cedar, west	ern red	23	
	/5		Cypress, sou	uthern	32	
Concrete, Perille	35-50		Douglas Fir		34	
Concrete, Purnice	60-90 25 60		Fir, commer	LBS. PER CU. FT. 175 165 165 165 165 165 165 165 16		
Concrete, vermiculite	25-60		Hemlock		28-29	
			Maple, hard		42	
			Oak, white		47	
			Pine, northe	ern	25	
MORTAR & PLASTER	LBS. PER C	U. FT.	Pine, southe	ern	29	
			Pine, ponde	rosa	28	
Mortar, masonry	11	6	Pine, short l	eaf southern	36	
Plaster, gypsum, sand	10-	4-120	Poplar, vello	W	28	
Plaster, gypsum, perlite	50-	-55	Redwood		28	
Plaster, Portland Cement, san	d 10-	4-120	Walnut, blad	Redwood Walput black		
Plaster, Portland Cement per	ite 50	-55			50	
Plaster Portland Cement ver	miculite 50	-55				
			METALS		LBS. PER CU. FT.	
BRICK & BLOCK (INCL MORTAR	) LBS. P	PER SQ. FT.	Aluminum,	cast	165	
			Brass, red		546	
4" Brick work		35	Brass, yellow	v, extruded bronze	528	
4" Concrete block stone or gr	avel	34	Bronze, con	nmercial	552	
4" Concrete block lightwt. ag	gregate (avg.)	22	Bronze, stat	Bronze, statuary		
6" Concrete block stone or gr	avel	50	Copper, cas	Copper, cast or rolled		
6" Concrete block lightwt. ag	gregate (avg.)	31	lron, cast gr	450		
8" Concrete block stone or gr	avel	58	Iron, wroug	ht	485	
8" Concrete block lightwt. ag	gregate (avg.)	36	Lead		710	
12" Concrete block stone or g	gravel	90	Monel		552	
12" Concrete block lightwt. a	ggregate (avg.)	58	Nickel		555	
			Stainless ste	eel, rolled	492-510	
			Steel, rolled		490	
SOIL, SAND & GRAVEL	LBS. PER CU. FT.	•	Zinc, rolled	or cast	440	
Cinder & ashes	40-45					
Clay, damp & plastic	110		REBAR	DIAMETER	LBS. PER FT.	
Clay, dry	63					
Clay & gravel dry	100		No. 3	.375"	.376	
Farth, dry & loose	76		No. 4	.500	.668	
Earth, dry & packed	95		No. 5	.625	1.043	
Farth, moist & loose	78		No. 6	.750	1.502	
Earth, moist & packed	96		No. 7	.875	2.044	
Farth, mud, packed	115		No. 8	1.000	2.670	
Sand or gravel, dry & loose	90-105		No. 9	1.128	3.400	
Sand or gravel, dry & packed	100-120	)	No. 10	1.270	4.303	
Sand or garvel, dry & wet	118-120	, )	No. 11	1.410	5.313	
cana or garren ary a wet	110-120		No. 14	1.693	7.650	

No. 18

2.257

13.600

# NOTES


This guide is offered by Diamond Products with the hope that it will help speed the education of new employees, increase their professionalism and advance our industry.

![](_page_31_Picture_1.jpeg)

![](_page_31_Picture_2.jpeg)

![](_page_31_Picture_3.jpeg)